

PORPHYRIN COMPOUND, AND
ELECTROPHOTOGRAPHIC PHOTOSENSITIVE MEMBER,
PROCESS-CARTRIDGE AND APPARATUS USING THE COMPOUND

5 FIELD OF THE INVENTION AND RELATED ART.

The present invention relates to a porphyrin compound inclusive of a porphyrinato-zinc compound having a novel crystal form, an electrophotographic photosensitive member using such a porphyrin compound,
10 and a process-cartridge and an electrophotographic apparatus including the photosensitive member.

Lasers currently used as exposure light sources in electrophotographic apparatus are predominantly semiconductor lasers having an
15 oscillating wavelength around 800 nm or 680 nm.

In recent years, various approaches for realizing higher resolutions have been made so as to comply with increasing demands for output images of a higher image quality. The laser wavelengths are also
20 concerned with realizing of the high resolution, and a shorter laser oscillation wavelength allows a smaller laser spot diameter facilitating a higher resolution electrostatic latent image formation.

Various proposals have been made for
25 realizing shorter laser oscillation wavelengths.

One of such proposal is to reduce a laser light wavelength into a half by utilizing second

harmonic generation (SHG) (JP-A 9-275242, JP-A 9-189930 and JP-A 5-313033). According to these proposals, GaAs laser and YAG laser already technically established and capable of high output power can be used as primary light sources, thus being able to realize a longer life or a larger output power.

Another proposal is to use wide-gap semiconductors, which allow a smaller size of device compared with the devices utilizing second harmonic generation. Lasers using ZnSe semiconductor (JP-A 7-321409 and JP-A 6-334272) and GaN semiconductor (JP-A 8-88441 and JP-A 7-335975) have been studied frequently in view of their high luminescence efficiency.

Such a semiconductor laser has posed difficulties in optimization of device structure, crystal growth conditions, electrodes, etc., and a long term oscillation at room temperature which is essential for commercialization has been obstructed due to occurrence of crystal defects, etc.

However, along with a technical innovation of substrates, etc., a report has been made on continuous oscillation for 1150 hours of a GaN semiconductor laser (at 50 °C) in October 1997 from Nichia Kagaku Kogyo K.K., and a commercialization thereof is near at hand.

On the other hand, in electrophotographic photosensitive members used in conventional laser-equipped electrophotographic apparatus, charge-generating materials having a large absorption band and showing a practical sensitivity characteristic
5 around 700 - 800 nm have been used, inclusive of non-metallic phthalocyanine, copper phthalocyanine and oxytitanium phthalocyanine, as specific examples.

However, such a charge-generating substance
10 for long-wavelength lasers does not have a sufficient absorption band around 400 - 500 nm or, if any, is encountered with a difficulty in stably exhibiting a sufficient sensitivity due to a strong wavelength-dependence.

15 JP-A 9-240051 has disclosed an electrophotographic photosensitive member having a single layer-type photosensitive layer or a laminate-type photosensitive layer including a charge generation layer using a charge-generating material
20 comprising an α -form oxytitanium phthalocyanine as an electrophotographic photosensitive member suitable for a laser of 400 - 500 nm. According to our study, however, the use of the charge-generating material is accompanied with not only a low sensitivity but also a
25 problem of resulting in an electrophotographic photosensitive member showing a large potential fluctuation in repetitive use due to a very large

memory characteristic for light around 400 nm.

As for porphyrin compounds, JP-A 63-106662 has disclosed an electrophotographic photosensitive member using a 5,10,15,20-tetraphenyl-21H,23H-porphyrin compound in its charge generation layer, but has not succeeded in providing a commercial level of sensitivity characteristic.

Further, JP-A 5-333575 mentions tetrapyrrolyl-porphyrin as an example of an N-type conductive pigment to be used in combination with a phthalocyanine compound for providing a charge-generating material but contains no specific further description about the tetrapyrrolyl porphyrin.

For reference, syntheses of porphyrin compounds have been reported in, e.g., 1) H. Fisher and W. Glein, ANN. Chem. 521,157 (1936); 2) R. Rothmund, J. Amer. Chem. Soc., 58,525 (1936); 3) A. Adler, F. Longo, F. Kampas and J. Kim., J. Inorg. Nucl. Chem. 32,2442 (1970); and 4) A. Shamin, P. Worthington and P. Hambright, J. Chem. Soc. Pak. 3(1), p. 1-3 (1981).

SUMMARY OF THE INVENTION

An object of the present invention is to provide a porphyrin compound suitable for use as a charge-generating material in an electrophotographic photosensitive member.

A more specific object of the present invention is to provide a tetrapyrrolyl-porphyrin compound, particularly a tetrapyrrolyl porphyrinato-zinc compound having a novel crystal form.

5 Another object of the present invention to provide an electrophotographic photosensitive member showing a high sensitivity in a wavelength region of 380 - 500 nm by using such a tetrapyrrolyl-porphyrin compound.

10 Further objects of the present invention are to provide a process-cartridge and an electrophotographic apparatus equipped with such an electrophotographic photosensitive member.

 According to the present invention, there is
15 provided a 5,10,15,20-tetrapyrrolyl-21H,23H-porphyrinato-zinc compound having a crystal form selected from the group consisting of (a), (b) and (c) shown below:


 (a) a crystal form characterized by peaks at
20 Bragg angles ($2\theta \pm 0.2$ deg.) of 9.4 deg., 14.2 deg. and 22.2 deg.,

 (b) a crystal form characterized by peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 7.0 deg., 10.5 deg. and 22.4 deg., and

25 (c) a crystal form characterized by peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 7.4 deg., 10.2 deg and 18.3 deg.,

respectively in CuK_α -characteristic X-ray diffraction patterns.

According to another aspect of the present invention, there is provided an electrophotographic photosensitive member, comprising a support and a photosensitive layer disposed on the support, wherein the photosensitive layer contains a porphyrin compound having a structure represented by formula (1) shown below:



wherein M denotes a hydrogen atom or a metal capable of having an axial ligand; R^{11} and R^{18} independently denote a hydrogen atom, an alkyl group capable of having a substituent, an aromatic ring capable of having a substituent, an amino group capable of having a substituent, a sulfur atom capable of having a substituent, an alkoxy group, a halogen atom, a nitro group or a cyano group; and A^{11} to A^{14} independently denote a hydrogen atom, an alkyl group capable of

having a substituent, an aromatic ring capable of
having a substituent or a heterocyclic ring capable of
having a substituent with the proviso that at least
one of A¹¹ to A¹⁴ is a heterocyclic group capable of
5 having a substituent.

The present invention further provides a
process-cartridge and an electrophotographic apparatus
equipped with the above-mentioned electrophotographic
photosensitive member.

10 These and other objects, features and
advantages of the present invention will become more
apparent upon a consideration of the following
description of the preferred embodiments of the
present invention taken in conjunction with the
15 accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a schematic illustration of an
electrophotographic apparatus equipped with a
20 photosensitive member of the invention.

Figures 2 and 3 are respectively a schematic
illustration of an electrophotographic apparatus
equipped with a process-cartridge including a
photosensitive member of the invention.

25 Figure 4 is a schematic illustration of an
electrophotographic apparatus equipped with a first
process-cartridge including a photosensitive member of

the invention, and also a second process-cartridge.


Figures 5 to 13 are CuK_α -characteristic X-ray diffraction patterns of 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrin crystals obtained in Synthesis Examples 3 to 11, respectively.

Figures 14 to 16 are CuK_α -characteristic X-ray diffraction patterns of 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrin crystals obtain in Examples 1-1 to 1-3, respectively.

Figure 17 is a CuK_α -characteristic X-ray diffraction pattern of 5,10,15,20-tetraphenyl-21H,23H-porphyrin crystal used in Comparative Example 2.


DETAILED DESCRIPTION OF THE INVENTION

The porphyrin compound used in the electrophotographic photosensitive member of the present invention has a structure represented by formula (1) shown below:



In the above formula, M denotes hydrogen atoms or a metal capable of having an axial ligand, i.e., a ligand coordinating to the metal M in a direction perpendicular to or intersecting with the porphyrin ring plane.

In the case where M is hydrogen atoms, the formula (1) is reduced to formula (1A) shown below:



Examples of the metal M capable of having an axial ligand may include: Mg, Zn, Ni, Cu, V, Ti, Ga, Sn, In, Al, Mn, Fe, Co, Pb, Ge and Mo, and examples of the axial ligand may include: halogen atoms, oxygen atom, hydroxy group, alkoxy groups, amino group and alkylamino groups.

R^{11} to R^{18} independently denote a hydrogen atom, an alkyl group capable of having a substituent, an aromatic ring capable of having a substituent, an alkoxy group, a halogen atom, a nitro group or a cyano group.

Further, A¹¹ to A¹⁴ independently denote a hydrogen atom, an alkyl group capable of having a substituent, an aromatic ring capable of having a substituent or a heterocyclic ring capable of having a substituent with the proviso that at least one of A¹¹ to A¹⁴ is a heterocyclic group capable of having a substituent.

Examples of the alkyl group may include: methyl, ethyl, propyl and butyl. Examples the aromatic ring may include: benzene ring, naphthalene ring and anthracene ring. Examples of the alkoxy group may include: methoxy and ethoxy. Examples of the halogen atom may include: fluorine, chlorine, bromine and iodine. Examples of the heterocyclic ring may include: pyridine ring, thiophene ring, imidazole ring, pyrazine ring, triazine ring, indole ring, coumarin ring, fluorene ring, benzofuran ring, furan ring and pyran ring.

Examples of the optionally possessed substituent may include: alkyl groups, such as methyl, ethyl, propyl and butyl; alkoxy groups, such as methoxy and ethoxy; alkylamino groups, such as methylamino, dimethylamino and diethylamino; arylamino groups, such as phenylamino and diphenylamino; halogen atoms, such as fluorine, chlorine and bromine; hydroxy, nitro, cyano; and halomethyl groups, such as trifluoromethyl.

Among the porphyrin compounds represented by the above-mentioned formula (1), it is preferred to use a 5,10,15,20-tetrapyridyl-21H,23H-porphyrin compound corresponding to the case where each of A¹¹ and A¹⁴ is a pyridyl group. It is particularly preferred to use a 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrin compound obtained in the case where each pyridyl group is 4-pyridyl group.

Among the 5,10,15,20-tetrapyridyl-21H,23H-porphyrin compounds, it is preferred to use 5,10,15,20-tetrapyridyl-21H,23H-porphyrin compounds having a crystal form characterized by a CuK_α-characteristic X-ray diffraction pattern showing a peak at a Bragg angle 2θ of 20.0±1.0 deg. inclusive of: 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrin compound having a crystal form characterized by peaks at Bragg angles (2θ±0.2 deg.) of 8.2 deg., 19.7 deg., 20.8 deg., and 25.9 deg.; 5,10,15,20-tetra(3-pyridyl)-21H,23H-porphyrin compound having a crystal form characterized by peaks at Bragg angles (2θ±0.2 deg.) of 7.1 deg., 8.4 deg., 15.6 deg., 19.5 deg., 21.7 deg., 22.4 deg. and 23.8 deg.; and 5,10,15,20-tetra(2-pyridyl)-21H,23H-porphyrin compound having a crystal form characterized by a Bragg angle (2θ±0.2 deg.) of 20.4 deg, respectively in CuK_α-characteristic X-ray diffraction patterns. Among the above, 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrin compound having a

crystal form characterized by peaks at Bragg angle
($2\theta \pm 0.2$ deg.) of 8.2 deg., 19.7 deg., 20.8 deg. and
25.9 deg. in a CuK_α -characteristic X-ray diffraction
pattern herein called (Crystal E), is particularly
5 preferred.

Further, among the 5,10,15,20-tetra(4-
pyridyl)-21H,23H-porphyrin compounds, a 5,10,15,20-
tetra(4-pyridyl)-21H,23H-porphyrinato-zinc compound is
preferred. It is particularly preferred to use a
10 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrinato-zinc
compound having a crystal form selected from:

(a) a crystal form characterized by peaks at
Bragg angles ($2\theta \pm 0.2$ deg.) of 9.4 deg., 14.2 deg. and
22.2 deg. (herein called Crystal A),

15 (b) a crystal form characterized by peaks at
Bragg angles ($2\theta \pm 0.2$ deg.) of 7.0 deg., 10.5 deg. and
22.4 deg. (Crystal B),


(c) a crystal form characterized by peaks at
Bragg angles ($2\theta \pm 0.2$ deg.) of 7.4 deg., 10.2 deg and
20 18.3 deg. (Crystal C), and

(d) a crystal form characterized by peaks at
Bragg angles ($2\theta \pm 0.2$ deg.) of 9.1 deg., 10.6 deg.,
11.2 deg. and 14.5 deg. (Crystal D)
respectively in CuK_α -characteristic X-ray diffraction
25 patterns.

Hereinbelow, some examples of the porphyrin
compound used in the electrophotographic


photosensitive member of the present invention are enumerated with their structural formulae, but they are not exhaustive.

5



(1 - 1)


10



(1 - 2)

15


20



(1 - 3)


25

5



(1 - 4)


10



(1 - 5)

15


20



(1 - 6)


25

5



(1 - 7)


10



(1 - 8)

15


20



(1 - 9)


25

5



(1 - 1 0)


10



(1 - 1 1)

15


20



(1 - 1 2)

25

5




(1-13)

10

15

20

25



(1-14)

The 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrinato-zinc compound having a crystal form characterized by peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 9.4 deg., 14.2 deg. and 22.2 deg. in a CuK_α -characteristic X-ray pattern (Crystal A) may be formed by subjecting 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrinato-zinc compound obtained by reaction under heating of metal-free 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrin compound with a zinc compound, such as zinc chloride, to conversion into an amorphous form by dry-milling together with glass beads in a sand mill, a paint shaker, etc., and then milling or stirring in the presence of a halide solvent, such as methylene chloride or chloroform.

The 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrinato-zinc compound having a crystal form characterized by peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 7.0 deg., 10.5 deg., 17.8 deg. and 22.4 deg. in a CuK_α -characteristic X-ray pattern (Crystal B) may be formed by subjecting 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrinato-zinc compound obtained by reaction under heating of metal-free 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrin compound with a zinc compound, such as zinc chloride, to conversion into an amorphous form by dry-milling together with glass beads in a sand mill, a paint shaker, etc., and then milling or stirring in the presence of an amide

solvent such as N,N-dimethylformamide or N-methylpyrrolidone.

5 The 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrinato-zinc compound having a crystal form characterized by peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 7.4 deg., 10.2 deg. and 18.3 deg. in a $\text{CuK}\alpha$ -characteristic X-ray pattern (Crystal C) may be formed by subjecting 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrinato-zinc compound obtained by reaction under
10 heating of metal-free 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrin compound with a zinc compound, such as zinc chloride, to conversion into an amorphous form by dry-milling together with glass beads in a sand mill, a paint shaker, etc., and then milling or
15 stirring in the presence of an alcohol solvent, such as methanol, ethanol or propanol.

Herein, "milling" means a grinding treatment together with dispersion media, such as glass beads, steel beads or alumina beads, and "stirring" means a
20 stirring without using such dispersion media.

Hereinbelow, the use of the porphyrin compound as a charge-generating material in the electrophotographic photosensitive member of the present invention will be described.

25 The electrophotographic photosensitive member according to the present invention may have a laminar structure including a single photosensitive layer

containing both a charge-generating material and a charge-transporting material formed on an electroconductive support, or alternatively a laminar photosensitive layer including a charge generation layer containing a charge-generating material and a charge transport layer containing a charge-transporting material formed successively on a support. The order of lamination of the charge generation layer and the charge transport layer can be reversed.

The support may comprise any material exhibiting electroconductivity, examples of which may include: metals, such as aluminum and stainless steel. In addition, it is also possible to use a substrate of plastic (such as polyethylene, polypropylene, polyvinyl chloride, polyethylene terephthalate, acrylic resin or polyethylene fluoride) coated with a vacuum-deposited film of aluminum, aluminum alloy, indium oxide, tin oxide or indium tin oxide; a substrate of plastic or above-mentioned support material coated with a layer of electroconductive particles (of e.g., aluminum, titanium oxide, tin oxide, zinc oxide, carbon black or silver) together with an appropriate binder resin; a plastic or paper support impregnated with electroconductive particles; or a plastic support comprising an electroconductive polymer. The support may assume a form of a cylinder,

or a flat, curved or wound sheet or belt. It is particularly suitable to use a cylindrical aluminum support in view of mechanical strength, electrophotographic performances and cost. A crude
5 aluminum pipe may be used as it is, or after treatments inclusive of physical treatments, such as honing, and chemical treatments, such as anodic oxidation or acid treatment.

Between the support and the photosensitive
10 layer, it is possible to dispose a primer layer or undercoating layer having a barrier function and an adhesive function. The undercoating layer may for example comprise a material, such as polyvinyl alcohol, polyethylene oxide, ethyl cellulose, methyl
15 cellulose, casein, polyamide (such as nylon 6, nylon 66, nylon 610, copolymer nylon or N-alkoxymethylated nylon), polyurethane, glue, aluminum oxide or gelatin. These materials may be dissolved or dispersed in an appropriate solvent to be applied onto the support,
20 thereby forming a film in a thickness of, preferably 0.1 - 10 μm , more preferably 0.5 - 5 μm .

The photosensitive layer of a single layer may be formed by mixing the porphyrin compound having a structure represented by the formula (1) as a
25 charge-generating material and a charge-transporting material in an appropriate binder resin solution to form a mixture liquid and applying the mixture liquid

onto the support, optionally via an undercoating layer as described above, followed by drying.

In the case of forming a laminar photosensitive layer as described above, the charge generation layer may suitably be formed by dispersing the porphyrin compound represented by the formula (1) in an appropriate binder solution to form a dispersion liquid and applying the dispersion liquid, followed by drying. However, the charge generating layer can also be formed by vapor deposition of the porphyrin compound.

The charge transport layer may be formed by applying and drying a paint formed by dissolving a charge-transporting material and a binder resin in a solvent. Examples of the charge-transporting material may include: triarylamine compounds, hydrazone compounds, stilbene compounds, pyrazoline compounds, oxazole compounds, thiazole compounds, and triarylmethane compounds.

Examples of the binder resin for constituting the above-mentioned photosensitive layer or constituent layers thereof may include: polyesters, acrylic resins, polyvinylcarbazole, phenoxy resins, polycarbonates, polyvinyl butyral, polystyrene, polyvinyl acetate, polysulfon, polyarylate, polyvinylidene chloride, acrylonitrile copolymer, and polyvinylbenzal.

The application of the photosensitive layer(s) may be performed by coating methods, such as dipping, spray coating, spinner coating, bead coating, blade coating and beam coating.

5 The single-layered photosensitive layer may have a thickness of 5 - 40 μm , preferably 10 - 30 μm . In the laminar photosensitive layer, the charge generation layer may have a thickness of 0.01 - 10 μm , preferably 0.05 - 5 μm , and the charge transport layer
10 may have a thickness of 5 - 40 μm , preferably 10 - 30 μm .

 The charge-generating material may preferably be contained in 20 - 90 wt. %, more preferably 50 - 80 wt. %, of the charge generation layer. The charge-
15 transporting material may preferably be contained in 20 - 80 wt. %, more preferably 30 - 70 wt. %, of the charge transport layer.

 The single-layered photosensitive layer may preferably contain 3 - 30 wt. % of the charge-
20 generating material and 30 - 70 wt. % of the charge-transporting material, respectively with respect to the total weight thereof.

 The porphyrin compound of the formula (1) can be used in mixture with another charge-generating
25 material if such is desired. In such cases, the porphyrin compound may preferably constitute at least 50 wt. % of the total charge-generating materials.

The photosensitive layer may be further coated with a protective layer as desired. Such a protective layer may be formed by applying a solution in an appropriate solvent of a resin, such as

5 polyvinyl butyral, polyester, polycarbonate resin (such as polycarbonate Z or modified polycarbonate), polyamide, polyimide, polyarylate, polyurethane, styrene-butadiene copolymer, styrene-acrylic acid copolymer or styrene-acrylonitrile copolymer onto a

10 photosensitive layer, followed by drying. The protective layer may preferably be formed in a thickness of 0.05 - 20 μm . The protective layer can contain electroconductive particles, an ultraviolet absorber or/and an anti-wearing agent. The

15 electroconductive particles may for example comprise particles of a metal oxide, such as tin oxide. The anti-wearing agent may for example comprise a fluorine-containing resin, alumina or silica.

Next, some embodiments of structure and

20 operation of the electrophotographic apparatus including an electrophotographic photosensitive member according to the present invention will be described.

Referring to Figure 1, a drum-shaped

25 photosensitive member 1 according to the present invention is driven in rotation at a prescribed peripheral speed in an indicated arrow direction about

a shaft 1a. During the rotation, the outer peripheral surface of the photosensitive member 1 is uniformly charged by charging means 2 at a prescribed positive or negative potential, and then exposed to light-image L (as by slit exposure or laser beam scanning exposure) by using an imagewise exposure means (not shown), whereby an electrostatic latent image corresponding to an exposure image is successively formed on the peripheral surface of the photosensitive member 1. The electrostatic latent image is then developed with a toner by developing means 4 to form a toner image on the photosensitive member 1. The toner image is transferred by corona transfer means 5 onto a recording material 9 which has been supplied from a paper supply unit (not shown) to a position between the photosensitive member 1 and the transfer means 5 in synchronism with the rotation of the photosensitive member 1. The recording material 9 carrying the received toner image is then separated from the photosensitive member surface and guided to an image fixing device 8 to fix the toner image. The resultant print or copy comprising the fixed toner image is then discharged out of the electrophotographic apparatus. The surface of the photosensitive member 1 after the image transfer is subjected to removal of the residual toner by a cleaning means 6 to be cleaned and then subjected to charge removal by a pre-exposure means 7,

to be recycled for repetitive image formation.

Figure 2 shows another embodiment of the electrophotographic apparatus wherein at least a photosensitive member 1, a charging means 2 and a developing means 4 are housed within a container 20 to form a process cartridge, which is detachably mountable or insertable to a main assembly of the electrophotographic apparatus along a guide means 12, such as a guide rail, provided to the main assembly. A cleaning means 6 disposed within the container 20 in this embodiment can be omitted or disposed outside the container 20.

On the other hand, as shown in Figures 3 and 4, it is possible to use a contact charging member 10 and cause the contact charging member 10 supplied with a voltage to contact the photosensitive member 1 to charge the photosensitive member. (This mode may be referred to as a "contact charging" mode.) In the apparatus shown in Figures 3 and 4, a toner image on the photosensitive member 1 is also transferred onto a recording material 9 by the action of a contact charging member 23. More specifically, the contact charging member 23 supplied with a voltage is caused to contact the recording material 9 to transfer the toner image on the photosensitive member 1 onto the recording material 9.

Further, in the apparatus shown in Figure 4,

at least the photosensitive member 1 and the contact charging member 10 are housed within a first container 21 to form a first process cartridge, and at least a developing means 4 is housed within a second container 22 to form a second process cartridge, so that the first and second process cartridges are detachably mountable to a main assembly of the apparatus. A cleaning means 6 can be disposed or not disposed within the container 21.

10 In case where the electrophotographic apparatus is used as a copying machine or a printer, exposure light image L may be given as reflected light from or transmitted light through an original, or by converting data read from the original into a signal and effecting a scanning by a semiconductor laser beam, etc., based on the signal.

The electrophotographic photosensitive member according to the present invention is applicable to a semiconductor laser having a short oscillation wavelength of 380 - 500 nm, preferably 400 - 450 nm.

Incidentally, the porphyrinato-zinc compounds having a novel crystal form exhibit an excellent function as a photoconductor and are applicable to not only an electrophotographic photosensitive member as mentioned above but also solar cells, sensors, switching devices, etc.

Her inbelow, the present invention will be

described more specifically based on Examples, to
which the scope of the present invention should not be
construed to be restricted. In the following
description, "part(s)" used for describing a relative
5 amount is by weight.

The X-ray diffraction data referred to herein
for determining the crystal form of related compounds
are based on data measured by X-ray diffractometry
using CuK_α characteristic X-rays according to the
10 following conditions:

Apparatus: Full-automatic X-ray diffraction
apparatus ("MXP18", available from MAC Science K.K.)

X-ray tube (Target): Cu

Tube voltage: 50 kV

15 Tube current: 300 mA

Scanning method: 2θ/θ scan

Scanning speed: 2 deg./min.

Sampling interval: 0.020 deg.

Starting angle (2θ): 5 deg.

20 Stopping angle (2θ): 40 deg.

Divergence slit: 0.5 deg.

Scattering slit: 0.5 deg.

Receiving slit: 0.3 mm

Curved monochromator: used.

25 Further, IR (infrared spectrometry) data
described herein are based on measurement by using
"FT/IR-420" (trade nam , made by Nippon Bunko K.K.),

and elementary analysis data are based on measurement by using "FLASH EA1112" (trade name, made by Thermo Quest Co.).

5 Various porphyrin compounds were prepared in the following Synthesis Examples 1 - 11 which were performed with reference to reports of A. Shamin, P. Worthington and P. Hambright, J. Chem. Soc. Pak. 3(1), p. 1 - 3 (1981); etc.

<Synthesis Example 1>

10 To 150 parts of propionic acid placed in a three-necked flask and under refluxing, 4 parts of pyridine-4-aldehyde and 2.8 parts of pyrrole were added dropwise and little by little through two dropping funnels. After the dropwise addition, the
15 system was further subjected to 30 min. of refluxing. The solvent was distilled off under a reduced pressure, and the residue together with a small amount of triethylamine added thereto was purified through a silica gel column with chloroform as the eluent to
20 obtain 1.1 parts of 5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrin, which exhibited the following elementary analysis and IR data:

	<u>Measured</u>	<u>Calculated</u>
25 C (%)	75.7	77.7
H (%)	4.5	4.2
N (%)	17.7	18.1

IR (KBr) peaks: 3467, 1593, 1400, 1068, 970 cm^{-1} .

<Synthesis Example 2>

1 part of 5,10,15,20-tetra(4-pyridyl)-
21H,23H-porphyrin and 1 part of zinc chloride were
added to 100 parts of N,N-dimethylformamide, and the
5 mixture was subjected to 1 hour of refluxing. After
distilling off the solvent under a reduced pressure,
the residue was purified through an aluminum column
with chloroform as the eluent to obtain 1 part of
5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrinato-zinc
10 compound, which exhibited the following elementary
analysis and IR data:

	<u>Measured</u>	<u>Calculated</u>
C (%)	66.1	70.4
H (%)	4.0	3.6
15 N (%)	15.6	16.4

IR (KBr) peaks: 1595, 993 cm^{-1} .

<Synthesis Example 3>

5 parts of the porphyrin compound obtained in
Synthesis Example 1 was dissolved in 150 parts of
20 conc. sulfuric acid at 5 °C, and the solution was
added dropwise to 750 parts of iced water under
stirring to result in a re-crystallizate, which was
filtered and subjected to four times of dispersion
washing within deionized water, followed by vacuum
25 drying at 40 °C to obtain 3.5 parts of 5,10,15,20-
tetra(4-pyridyl)-21H,23H-porphyrin crystal (called
Crystal E). Crystal E exhibited the same IR data as

the porphyrin compound of Synthesis Example 1 and provided a CuK_α -characteristic X-ray diffraction pattern of Figure 5 showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 8.2 deg., 19.6 deg., 20.7 deg. and 25.9 deg.

<Synthesis Example 4>

0.5 part of Crystal E obtained in Synthesis Example 3 was subjected to dispersion together with 15 parts of tetrahydrofuran and 15 parts of 1 mm-dia. glass beads for 24 hours in a paint shaker, and then recovered by filtration and dried to obtain a product which was again a type of Crystal E providing a CuK_α -characteristic X-ray diffraction pattern of Figure 6 showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 8.2 deg., 19.6 deg., 20.7 deg. and 25.9 deg.

<Synthesis Example 5>

0.5 part of Crystal E obtained in Synthesis Example 3 was subjected to dispersion together with 15 parts of chloroform and 15 parts of 1 mm-dia. glass beads for 24 hours in a paint shaker, and then recovered by filtration and dried to obtain a product which was again a type of Crystal E providing a CuK_α -characteristic X-ray diffraction pattern of Figure 7 showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 8.2 deg., 19.6 deg., 20.7 deg. and 25.9 deg.

<Synthesis Example 6>

0.5 part of Crystal E obtained in Synthesis

Example 3 was subjected to dispersion together with 15 parts of N,N-dimethylformamide and 15 parts of 1 mm-dia. glass beads for 24 hours in a paint shaker, and then recovered by filtration and dried to obtain a product which was again a type of Crystal E providing a CuK_α -characteristic X-ray diffraction pattern of Figure 8 showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 8.2 deg., 19.6 deg., 20.7 deg. and 25.9 deg.

<Synthesis Example 7>

0.5 part of Crystal E obtained in Synthesis Example 3 was subjected to dispersion together with 15 parts of 1 mm-dia. glass beads for 24 hours in a paint shaker, and then recovered by aqueous ultrasonic treatment (i.e., ultrasonic dispersion in an aqueous medium) and filtration and dried to obtain a product which was again a type of Crystal E providing a CuK_α -characteristic X-ray diffraction pattern of Figure 5 showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 9 deg., 19.8 deg., 20.7 deg. and 25.9 deg.

<Synthesis Example 8>

0.5 part of Crystal E obtained in Synthesis Example 3 was subjected to dispersion together with 15 parts of methanol and 15 parts of 1 mm-dia. glass beads for 24 hours in a paint shaker, and then recovered by filtration and dried to obtain a product which was again a type of Crystal E providing a CuK_α -characteristic X-ray diffraction pattern of Figure 10

showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 8.2 deg., 19.7 deg., 20.8 deg. and 25.9 deg.

<Synthesis Example 9>

0.5 part of Crystal E obtained in Synthesis
5 Example 6 was subjected to dispersion together with 15
parts of 1 mm-dia. glass beads for 24 hours in a paint
shaker, and then recovered by aqueous ultrasonic
treatment and filtration and dried to obtain a product
which was again a type of Crystal E providing a CuK_α -
10 characteristic X-ray diffraction pattern of Figure 11
showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 8.3
deg., 19.7 deg., 20.7 deg. and 25.8 deg.

<Synthesis Example 10>

0.5 part of porphyrinato-zinc compound
15 obtained in Synthesis Example 2 was subjected to
dispersion together with 15 parts of 1 mm-dia. glass
beads for 24 hours in a paint shaker, and then
recovered by aqueous ultrasonic treatment and
filtration and dried to obtain an amorphous
20 5,10,15,20-tetra(4-pyridyl)-21H,23H porphyrinato-zinc
compound providing a CuK_α -characteristic X-ray
diffraction pattern of Figure 12 showing no clear
peaks.

<Synthesis Example 11>

25 0.5 part of the porphyrinato-zinc compound
obtained in Synthesis Example 10 was subjected to
dispersion together with 15 parts of tetrahydrofuran

and 15 parts of 1 mm-dia. glass beads for 24 hours in a paint shaker, and then recovered by filtration and dried to obtain a product which was a type of Crystal D providing a CuK_α -characteristic X-ray diffraction pattern of Figure 13 showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 9.1 deg., 10.5 deg., 11.2 deg. and 14.5 deg.

(Example 1-1)

0.5 part of the porphyrinato-zinc compound obtained in Synthesis Example 10 was subjected to dispersion together with 15 parts of chloroform and 15 parts of 1 mm-dia. glass beads for 24 hours in a paint shaker, and then recovered by filtration and dried to obtain a product which was a type of Crystal A providing a CuK_α -characteristic X-ray diffraction pattern of Figure 14 showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 9.4 deg., 14.2 deg. and 22.2 deg.

(Example 1-2)

0.5 part of the porphyrinato-zinc compound obtained in Synthesis Example 10 was subjected to dispersion together with 15 parts of N,N-dimethylformamide and 15 parts of 1 mm-dia. glass beads for 24 hours in a paint shaker, and then recovered by filtration and dried to obtain a product which was a type of Crystal B providing a CuK_α -characteristic X-ray diffraction pattern of Figure 15 showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 7.0

deg., 10.5 deg., 17.8 deg. and 22.4 deg.

(Example 1-3)


0.5 part of the porphyrinato-zinc compound obtained in Synthesis Example 10 was subjected to
5 dispersion together with 15 parts of methanol and 15 parts of 1 mm-dia. glass beads for 24 hours in a paint shaker, and then recovered by filtration and dried to obtain a product which was a type of Crystal C providing a CuK_α -characteristic X-ray diffraction
10 pattern of Figure 16 showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 7.4 deg., 10.2 deg. and 18.3 deg.
(Example 2-1)

5 parts of methoxymethylated nylon (Mav (average molecular weight) = 32000) and 10 parts of
15 alcohol-soluble copolymer nylon (Mav = 29000) were dissolved in 95 parts of methanol to obtain a coating liquid, which was applied by means of a wire bar onto an aluminum sheet of 15 cm x 20 cm and dried to form a 0.5 μm -thick undercoating layer.

20 Then, 4 parts of Crystal E (5,10,15,20-tetra(4-pyridyl)-21H,23H-porphyrinato-zinc crystal) obtained in Synthesis Example 3 was added to a solution of 2 parts of polyvinylbutyral resin ("BX-1", made by Sekisui Kagaku Kogyo K.K.) in 100 parts of
25 cyclohexanone, and the mixture was subjected to 3 hours of dispersion in a paint shaker, followed by dilution with 150 parts of ethyl acetate, to obtain a

dispersion liquid, which was then applied by a wire bar over the undercoating layer and dried to form a 0.2 μm -thick charge generation layer.

Then, 5 parts of triphenyl compound represented by a formula shown below:




and 5 parts of polycarbonate resin ("IUPILON Z200", made by Mitsubishi Engineering-Plastics K.K.), were dissolved in 35 parts of chlorobenzene to obtain a coating liquid, which was applied by a wire bar over the charge generation layer and dried to form a 20 μm -thick charge transport layer, thereby obtaining an electrophotographic photosensitive member.

(Examples 2-2 to 2-12)

Eleven photosensitive members were prepared in the same manner as in Example 2-1 except for using porphyrin compounds or crystals prepared in Examples or Synthesis Examples shown in Table 1 appearing hereinafter as the charge-generating material instead of Crystal E.


(Comparative Example 2-1)

A photosensitive member was prepared in the same manner as in Example 2-1, except for using Comparative Azo Compound A having a structure shown below:



10 (Comparative Example 2-2)

A photosensitive member was prepared in the same manner as in Example 2-1 except for using Comparative Porphyrin Compound B having a structure shown below (i.e., 5,10,15,20-tetraphenyl-21H,23H-porphyrin) obtained in the same manner as in Synthesis Example 1 except for using benzaldehyde instead of the pyridine-4-aldehyde and giving a CuK_α -characteristic X-ray diffraction pattern of Figure 17 showing peaks at Bragg angles ($2\theta \pm 0.2$ deg.) of 8.6 deg., 14.7 deg., 17.4 deg. as the charge-generating material instead of Crystal E.



[Sensitivity Test]

Each of the photosensitive members prepared in above Examples and Comparative Examples were subjected a sensitivity test as follows.

5 For the test, each photosensitive member was charged to an initial surface potential of -700 volts and exposed to monochromatic light having a wavelength of 403 nm obtained by passing light from a halogen lamp through an interference filter and transmitted
10 through an electroconductive NESA glass sheet of 10 cm² (for imparting the surface potential to the photosensitive member and measuring a surface potential after exposure of the photosensitive member) disposed in contact with the photosensitive member,
15 thereby measuring a half-attenuation exposure energy $E_{1/2}$ ($\mu\text{J}/\text{cm}^2$) required for lowering the surface potential to a half (-350 volts).

The results of the measurements are inclusively shown in Table 1 below.

20

25

Table 1

Example	Porphyrin compound		Half-attenuation energy $E_{1/2}$ at 403 nm [$\mu\text{J}/\text{cm}^2$]	
	Example	Crystal		
5	2-1	Synthesis 3	E	2.36
	2-2	Synthesis 4	E	1.27
	2-3	Synthesis 5	E	1.69
	2-4	Synthesis 6	E	1.19
	2-5	Synthesis 7	E	0.86
10	2-6	Synthesis 8	E	1.23
	2-7	Synthesis 9	E	1.01
	2-8	Synthesis 10	amorphous	4.78
	2-9	Synthesis 11	D	14.9
	2-10	1-1	A	6.23
15	2-11	1-2	B	8.52
	2-12	1-3	C	8.59
Comp. 2-1	Comp. Compd. A *1	-	94	
Comp.	Comp. Compd. B *2	-	*3	

20

*1: Azo compound.

*2: Metal-free tetraphenyl-porphyrin compound.

*3: The measurement of $E_{1/2}$ was impossible

because substantially no surface potential lowering was

25 caused by the exposure.

(Example 3-1)

An electroconductive paint was prepared by
subjecting a mixture of 50 parts of titanium oxide
powder coated with 10 %-antimony oxide-containing tin
5 oxide, 25 parts of resol-type phenolic resin, 20 parts
of methyl cellosolve, 5 parts of methanol and 0.002
part of silicone oil (polydimethylsiloxane-
polyoxyalkylene copolymer, $M_{av} = 3000$) to 2 hours of
dispersion together with 1.2 mm-dia. glass beads in a
10 sand mill.


A 62 mm-dia. aluminum cylinder was coated
with the above-prepared electroconductive paint by
dipping and dried for 30 min. at 140 °C to form a 16
µm-thick electroconductive layer.

15 A solution of 5 parts of 6-66-61-12
quaternary polyamide copolymer resin in a mixture
solvent of 70 parts of methanol and 25 parts of
butanol was applied by dipping on the
electroconductive layer, and dried to form a 0.6 µm-
20 thick undercoating layer.

Then, 2.5 parts of Crystal E prepared in
Synthesis Example 7 and 1 part of polyvinylbutyral
resin ("ESLEC BX-1", made by Sekisui Kagaku Kogyo
K.K.) were added to 50 parts of cyclohexanone, and the
25 mixture was dispersed for 6 hours together with 1.2
mm-dia. glass beads in a sand mill, followed by
dilution with 40 parts of cyclohexanone and 60 parts

of ethyl acetate to obtain a paint, which was then applied by dipping onto the undercoating layer and dried for 20 min. at 130 °C to form a 0.20 μm-thick charge generation layer.

5 Then, 8 parts of the triphenylamine compound used in Example 2-1 and 1 part a triphenylamine compound represented by a formula shown below:



were dissolved together with polycarbonate resin ("IUPILON Z400", made by Mitsubishi Engineering-Plastics K.K.) in a mixture solvent of 70 parts of monochlorobenzene and 30 parts of methylal to form a paint, which was applied by dipping on the charge generation layer and dried for 1 hour at 110 °C to form a 17 μm-thick charge transport layer, thereby obtaining an electrophotographic photosensitive member.

15

20

The thus-prepared photosensitive member was incorporated in a commercially available laser beam printer ("COLOR LASER SHOT-LBP 2360", made by Canon K.K.) after remodeling of replacing the laser unit with a violet, semiconductor laser having an oscillation wavelength of 405 nm ("VIOLET LASER

25

DIODE", made by Nichia Kagaku Kogyo K.K.) together
with an associated optical system, and subjected to
image formation. As a result, images having a high
resolution and good gradation characteristic were
5 obtained.

As described above, according to the present
invention, a porphyrin compound having a specific
structure is incorporated in a photosensitive layer to
provide an electrophotographic photosensitive member
10 which can exhibit an excellent sensitivity when used
in combination with an exposure system including a
semiconductor laser having a short oscillation
wavelength of 380 - 500 nm. There are further
provided a process-cartridge and an
15 electrophotographic apparatus including such a
photosensitive member.

20

25